



PERFORMANCE GUIDE

Represents Typical Values Only

JK8011 – MACjet® Drum Matte White Kimdura® Ink Jet

Revised: 4/2016 AKB

Description	Applications and End Uses		
Product	JK8011 is a 5.0 mil matte ink jet printable coated white biaxially oriented polypropylene with a high tack cold temperature adhesive and a 3.2 semi-bleached calendared kraft liner. BS5609 Certified Section 2 and Section 3 with Epson C-831 & C3500; NeuraLabel 300x; & Primera LX2000.		
Face	A polypropylene film, matte coated to provide an excellent and durable ink jet printing surface. Designed for pigment base inkjet.		
	Physical Properties Without Adhesive		
	Caliper, inches	0.005 (5.0 mils)	ASTM D-2103
	Basis Weight, lbs. (24" x 36"/500 sheets)	70 +/- 10%	TAPPI T-410
	Tensile, ppiw	24 MD 20.5 CD	ASTM D-882
	Opacity (%)	90	TAPPI T-425
	Brightness	93	TAPPI T-452
Adhesive	Special Drum MF2030 adhesive is an aggressive cold temperature adhesive specifically developed to adhere to all types of metal and polyethylene drums, both new and reconditioned.		
	Physical Properties of Adhesive		
	Thickness, inches	0.0008 +/- 10%	
	Peel Adhesion, lbs./in.	1.9 lbs. or face delamination	PSTC-1 (30 min. applied)
	Minimum Application	-20°F (-29°C) on most surfaces	CTM #45 Curwood
	Service Ranges	-65°C to +200° F (-40 to +93°C)	Polyester Film Dry Surface
Liner	A semi-bleached calendared kraft liner excellent for die cutting, stripping and label dispensing. Primarily for roll -to -roll applications where a more demanding liner may be needed.		
	Caliper, inches	0.0032 +/- 10%	TAPPI T-411
	Basis Weight, lbs. (24" x 36"/500 sheets)	50 +/- 10%	TAPPI T-410

Shelf Life One year when stored at 72° F and 50% R.H.

This product complies with CONEG regulations.
This product meets the requirements of the Clean Air Act of 1990.

** NOTE: Ink jet print quality and durability are dependent upon the interworking of several elements such as the printer make/model, the type of inks used, the printer settings, and the facestock. Please test all applications.*

The user is responsible for determining the product's suitability for all aspects of the applications. If there are any questions about applications, ore regulatory compliances, please contact your Mactac sales representative to discuss your requirements for recommendations. If this is a printed Performance Guide, it is an uncontrolled document. Please check the Mactac website for the latest, most up-to-date version at www.mactac.com

CALL 1-800-548-3456 for additional product information

IMPORTANT NOTICE: The information given and the recommendations made herein are based on our research and are believed to be accurate, but no guarantee of their accuracy or completeness is made. In every case, user shall determine before using any product in full scale production, or in any way, whether such product is suitable for user's intended use for their particular purpose under their own operating conditions. User assumes all risk and liability whatsoever in connection with their use of any product. The products discussed herein are sold without any warranty as to merchantability or fitness for a particular purpose, or any other warranty, express or implied. No representative of ours has any authority to waive or change the foregoing provisions, and no statement or recommendation not contained herein shall have any force of effect unless in an agreement signed by the officers of seller and manufacturer. Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent without authority from the owner of the patent. The following is made in lieu of all warranties, express or implied: Seller's and manufacturer's only obligation shall be to replace or credit such quantity of the product proved to be defective at its discretion.

© Kimdura is a Registered Trademark of Neenah Paper, Inc.

