

www.Mactac.com

Version #3 (0217)
Approved by J. S.

Product

6700 Sparkle Metallic
High Performance Cast Vinyl Series

Product Description

Sparkle Metallic 6700 is a premium Mactac film designed for high profile applications over flat to complex curves like rivets, corrugations and other irregular surfaces. The face is a 3.0-mil cadmium-free cast vinyl with high gloss and a high concentration of metallic flakes resulting in rich, shimmering colors. The product is coated with a high-performance permanent, clear solvent acrylic adhesive protected with 78# bleached white kraft liner for good stability and layflat.

Typical Applications

- Logos
- Automotive applications
- Fleet marking
- Equipment identification
- Decals
- General signage

Physical Properties

Property	Typical Values	Test Method
Thickness in inches	0.0040 (101)	ASTM D-645
Peel Adhesion 180° on Stainless Steel - 30 min. - 24 hr.	2.8 (12.5) 4.0 (17.5)	ASTM D-903
Face Material Data, 68°F (20°C) Tensile strength lb. /in. (N/m) Elongation %	>7.5 (1300) >80%	DIN 53455
Dimensional Stability (shrinkage) in Percent	< 0.20	10" x10" Sample 48 hours @ 158°F bonded to aluminum
Temperature Ranges Application: End Use:	40° to 104°F (5° to 40°C) -50° to 225°F (-45° to 107°C)	

Shelf Life

Two years when stored between at 60- 80°F (15 - 25°C) and 50% relative humidity or less.

Durability

This product is good for 5-year in outdoor durability. This use-life estimate is based upon accelerated age studies based on vertical applications under “normal” temperate climates. Please note that exposure to severe temperatures, ultra-violet light and also tropical, sub-tropical or desert regions will cause more rapid deterioration. This also applies to polluted areas, high altitude and south facing exposure.

Chemical Resistance

A sample is prepared in the same manner as for the Chemical Resistance Test and is immersed in the test fluid followed by drying at each stage.

Test Fluid	Observation
Gasoline (30min)	No Effect
Distilled Water (24 hrs.)	No Effect
SAE 20 Motor Oil (1 hr.)	No Effect
10% HCL (10min)	No Effect
10% NH ₄ OH (10 min)	No Effect

Limitations

- 1) The user is responsible for determining the product’s suitability, including adhesion and if needed, removal characteristics when used in applications other than listed specifically in this Performance Guide.
- 2) If there are any questions about applications, please contact your Mactac sales representative to discuss your requirements for recommendations.
- 3) If this is a printed Performance Guide it is an uncontrolled document. Please check the Mactac website for the latest, most up-to-date version.

Application

Application of Sparkle Metallic 6700 is made easier if **Mactac** pre-spacing tape is used. Where exposures to chemical and solvent spills are likely to occur, edge sealing of decals with a varnish or clear coat will prevent edge lift. Correct varnishing of decals gives greater protection and longer end-use life against any prolonged effect of weathering, abrasion and other erosive effects such as frequent cleaning.

- *Values given are typical and are not necessarily for use in specification.*

CALL 1-800-321-8834 for additional product information

IMPORTANT NOTICE: The information given and the recommendations made herein are based on our research and are believed to be accurate, but no guarantee of their accuracy or completeness is made. In every case, user shall determine before using any product in full scale production, or in any way, whether such product is suitable for user’s intended use for their particular purpose under their own operating conditions. User assumes all risk and liability whatsoever in connection with their use of any product. The products discussed herein are sold without any warranty as to merchantability or fitness for a particular purpose, or any other warranty, express or implied. No representative of ours has any authority to waive or change the foregoing provisions, and no statement or recommendation not contained herein shall have any force of effect unless in an agreement signed by the officers of seller and manufacturer. Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent without authority from the owner of the patent. The following is made in lieu of all warranties, express or implied: Seller’s and manufacturer’s only obligation shall be to replace or credit such quantity of the product proved to be defective at its discretion.

™ Trademark of Morgan Adhesives Company LLC
© Registered Trademark of Morgan Adhesives Company LLC
www.Mactac.com

