

# PERFORMANCE GUIDE

## **IB1178XTPK Double Coated Tape**

Version: 1 Date: 8/2016 Approved by: JNP

## **Product Description**


IB1178XTPK consists of a .5mil PET carrier coated on both sides with 1.2 mils of aggressive rubber-based pressure sensitive adhesive. The adhesive is protected by a two-sided silicone coated 72# White Polycoated liner. This product is designed for general purpose bonding applications on semi-smooth surfaces and has excellent performance on LSE substrates.

## **Product Construction**

• Carrier: 0.5 mil PET

• Adhesive: 1.2 mils MP593XT Rubber

Liner: 72# White PCKWeb Width: 54"



## **Features**

- Aggressive rubber based adhesive.
- Excellent shear properties
- 72# White Poly-Coated Liner

#### **Benefits**

- High initial tack and adhesion
- Excellent adhesion to a wide variety of substrates
- Outstanding handling and diecutting.
- Performs well on most LSE surfaces
- Poly-coated liner offers excellent moisture resistance and stability.

## **Applications**

- General purpose mounting & bonding applications
- Foam Fabrication
- Felt and Fabric Bonding
- Appliance Assembly
- Building & Construction
- Automotive Interior
- Gasket Fabrication
- Insulation Installation

IB1178XTPK Physical Properties		
Mils	MM	Microns
Liner/Unwind	Liner/Unwind	Liner/Unwind
1.2/1.2	.0305/.0305	30.5/30.5
0.5	.0127	12.7
5.3	.1346	134.6
8.2	.2083	208.3
Test Method	Typical Values	
		Oz/in.
	Liner/Unwind	Liner/Unwind
Backed with 2 mil PET	12.0/12.0	192/192
	_	_
PSTC-101-Method A	_	Oz/in. Liner/Unwind
Stainless Steel	-	192/192
PSTC-107-Method A	Hours to Fail	
72°F	500+	
72°F	200+	
ASTM-D882	Lbs./in.	Oz./in.
	10	160
ASTM-D882	%	
	100	
ance		
Application Method	Result	
RT with 50% Compression	Aggressive Adhesion	
RT with 50% Compression	Foam Destruction	
RT with 50% Compression	Foam Destruction	
RT with 50% Compression	Foam Destruction	
	Mils Liner/Unwind  1.2/1.2  0.5  5.3  8.2  Test Method PSTC-16-Method A  Backed with 2 mil PET  PSTC-101-Method A  Stainless Steel  PSTC-107-Method A  72°F  72°F  72°F  ASTM-D882  ASTM-D882  ASTM-D882  ART with 50% Compression RT with 50% Compression RT with 50% Compression	Mils   Liner/Unwind   Liner/Unwind     1.2/1.2

Values given are typical and not for use in specifications

#### **SERVICE TEMPERATURE**

Application: Above 50°F (10°C) for best performance

End Use: -0°F to 180°F (-18°C to 82°C)

#### CHEMICAL RESISTANCE

Resistant to water, detergent and alcohol. Not recommended for use in contact with aliphatic or aromatic hydrocarbons.

## **APPLICATION DETAILS**

For best performance surfaces must be clean, dry and free of any oil, grease or other contaminant.

## **SHELF LIFE**

Two year shelf life when stored at 75°F. (24°C.) and 50% relative humidity or less. It is recommended that the product be stored in its original package until ready to use.

CALL 1-800-328-2619 for additional product information

**IMPORTANT NOTICE:** The information given and recommendations made herein are based on our research and are believed to be accurate. In every case, user shall determine before using any product in full scale production, whether such product is suitable for their particular purpose under their own operating conditions. User assumes all risk and liability whatsoever in connection with their use of any product. The products discussed herein are sold without any warranty as to merchantability or any other warranty, expressed or implied. No representative of ours has any authority to waive or change the foregoing provisions unless in a specific agreement signed by the officers of seller and manufacturer. Ultimately, sellers and manufacturers only obligation shall be to replace or credit such quantity of the product proved to be defective at its discretion.



<sup>™</sup> Trademark of Morgan Adhesives Company LLC

Registered Trademark of Morgan Adhesives Company LLC www.Mactac.com