



# PERFORMANCE GUIDE

Revised: 8/2016 JNP

**PRODUCT:** TM8102

## PRODUCT DESCRIPTION

TM8102 is a white spunlace nonwoven fabric coated on side with a skin friendly medical grade acrylic adhesive. The adhesive is protected by a 60# PCK release liner.

TM8102 was designed for use in applications where immediate adhesion to skin is required. Typical applications include electrode and sensor construction, ostomy, wound dressings, fixation devices, device coverings and surgical garments.

## PRODUCT CONSTRUCTION

**Carrier:** 2.4oz bright white polyester spunlace nonwoven fabric.

**Adhesive:** This medical grade acrylic adhesive has been formulated for sustained contact with human skin. It has been assessed by an independent bio-medical laboratory following ISO-10993 guidelines for skin contact properties. Specific test procedures and results are available upon request.

**Liner:** 60# poly-coated bleached Kraft with a silicone release coating on one side.

## PHYSICAL PROPERTIES

Values given are typical and are not for use in specifications.

Performance Test	Unit of Measure	Typical Values	Testing Method
<b>180° Peel Stainless Steel</b>			
30 minute dwell	<b>lbs./in width</b>	<b>5.5 (24.2)</b>	<b>PSTC – 101 (Method A)</b>
24 hour dwell	<i>(N/25mm)</i>	<b>6.43 (28.3)</b>	
<b>Loop Tack</b>	<b>lbs./in<sup>2</sup> (N/25mm)</b>	<b>2.6 (11.4)</b>	<b>PSTC - 16</b>
<b>Shear 1kg @ 72°F</b>	<b>hours</b>	<b>1</b>	<b>PSTC – 107</b>
<b>Thickness</b>			
Carrier & Adhesive	<b>inches (microns)</b>	<b>.0156 (396.7)</b>	
Liner		<b>.0046 (78.7)</b>	

## **TEMPERATURE RANGE**

This product is intended for use at ambient temperatures.

## **ATTRIBUTES**

- Intended for long term use (3 – 5 days)
- Conformable
- Excellent adhesion properties
- Aqueous solution resistant
- Sterilizable by ETO, gamma and autoclave

## **SHELF LIFE**

Two year shelf life when stored at 75°F. (24°C.) and 50% relative humidity or less. It is recommended that the product be stored in its original package until ready to use.

## **STATEMENT OF RECOMMENDATION**

This product should be tested thoroughly in final converted form under end-use conditions to ensure it meets the requirements of the specific application.

*\* Values given are typical for unprocessed product and are not for use as specifications. Processing may change the values.*

**CALL 1-800-255-9733 for additional product information**

**IMPORTANT NOTICE:** The information given and recommendations made herein are based on our research and are believed to be accurate. In every case, user shall determine before using any product in full scale production, whether such product is suitable for their particular purpose under their own operating conditions. User assumes all risk and liability whatsoever in connection with their use of any product. The products discussed herein are sold without any warranty as to merchantability or any other warranty, expressed or implied. No representative of ours has any authority to waive or change the foregoing provisions unless in a specific agreement signed by the officers of seller and manufacturer. Ultimately, sellers and manufacturers only obligation shall be to replace or credit such quantity of the product proved to be defective at its discretion.

™ Trademark of Morgan Adhesives Company LLC

® Registered Trademark of Morgan Adhesives Company LLC

www.Mactac.com

