



PERFORMANCE GUIDE

Represents Typical Values Only

www.Mactac.com



AC9512LF

Revised: 08/2019 CCF

Platinum™ Semi-Gloss for Prime Lay Flat

	Description	Applications and End Uses																														
Product	AC9512LF is a bright white semi-gloss coated litho construction with a permanent acrylic adhesive and layflat liner suitable for sheeting and die cutting.	Complies with pH, Toy Safety and photo neutrality and lay flat requirements for scrapbook, photo album stickers and similar applications.																														
Face	<p>Platinum Semi-Gloss is a very bright, white semi-gloss coated sheet with exceptional ink receptivity and high internal strength characteristics for high speed printing and converting.</p> <p>Physical Properties Without Adhesive</p> <table><tr><td>Caliper, inches</td><td>0.0030 +/- 10%</td><td>TAPPI T-411</td></tr><tr><td>Brightness % Reflectance at 75° angle</td><td>89</td><td>TAPPI T-452</td></tr><tr><td>Gloss % Reflectance at 75° angle</td><td>75</td><td>TAPPI T-480</td></tr><tr><td>Opacity</td><td>86</td><td>TAPPI T-425</td></tr><tr><td>Tear, grams</td><td>42 MD 50 CD</td><td>TAPPI T-414</td></tr><tr><td>Tensile, lbs./in.</td><td>36 MD 16 CD</td><td>TAPPI T-494</td></tr><tr><td>pH of face stock</td><td>+7</td><td>TAPPI T-509</td></tr><tr><td>Lignin</td><td>Less than 1%</td><td>ANSI /MISO Z39.48-1992</td></tr><tr><td>Basis Weight, lbs. (25" x 38"/500 sheets)</td><td>59 +/- 10%</td><td>TAPPI T-410</td></tr><tr><td>Toy Safety</td><td colspan="2">Complies ASTM F963-96a & Hasbro SRS-012 Rev F</td></tr></table>	Caliper, inches	0.0030 +/- 10%	TAPPI T-411	Brightness % Reflectance at 75° angle	89	TAPPI T-452	Gloss % Reflectance at 75° angle	75	TAPPI T-480	Opacity	86	TAPPI T-425	Tear, grams	42 MD 50 CD	TAPPI T-414	Tensile, lbs./in.	36 MD 16 CD	TAPPI T-494	pH of face stock	+7	TAPPI T-509	Lignin	Less than 1%	ANSI /MISO Z39.48-1992	Basis Weight, lbs. (25" x 38"/500 sheets)	59 +/- 10%	TAPPI T-410	Toy Safety	Complies ASTM F963-96a & Hasbro SRS-012 Rev F		
Caliper, inches	0.0030 +/- 10%	TAPPI T-411																														
Brightness % Reflectance at 75° angle	89	TAPPI T-452																														
Gloss % Reflectance at 75° angle	75	TAPPI T-480																														
Opacity	86	TAPPI T-425																														
Tear, grams	42 MD 50 CD	TAPPI T-414																														
Tensile, lbs./in.	36 MD 16 CD	TAPPI T-494																														
pH of face stock	+7	TAPPI T-509																														
Lignin	Less than 1%	ANSI /MISO Z39.48-1992																														
Basis Weight, lbs. (25" x 38"/500 sheets)	59 +/- 10%	TAPPI T-410																														
Toy Safety	Complies ASTM F963-96a & Hasbro SRS-012 Rev F																															
Adhesive	<p>ST95 is a permanent acrylic emulsion with aggressive initial tack, excellent ultimate adhesion and mandrel hold. Very good adhesion to corrugated, glass and various plastic substrates. Considered to be latex glove friendly for use in some healthcare applications.</p> <p>Physical Properties of Adhesive</p> <table><tr><td>Thickness, inches</td><td>0.0007 +/- 10%</td><td></td></tr><tr><td>Peel Adhesion, lbs./in.</td><td>2.6</td><td>PSTC-101F (30 min. applied)</td></tr><tr><td>pH of adhesive</td><td>+7*</td><td>Measured in liquid form</td></tr><tr><td>Photographic Activity Test</td><td>Passes</td><td>ISO 14523</td></tr><tr><td>LHAMA</td><td>16 CFR 1500.14(b)(8)</td><td>ASTM D4236</td></tr><tr><td>TRA</td><td>16 CFR 1500.3(b)(5) and (8)</td><td></td></tr><tr><td>Toy Safety</td><td colspan="2">Complies ASTM F963-96a & Hasbro SRS-012 Rev F</td></tr><tr><td>Temperature Ranges</td><td></td><td></td></tr><tr><td>Minimum Application</td><td>+25°F (-4°C)</td><td>CTM #45 Curwood</td></tr><tr><td>Service Ranges</td><td>-75°F to +200°F (-59°C to +93°C)</td><td>Polyester Film Dry Surface</td></tr></table>	Thickness, inches	0.0007 +/- 10%		Peel Adhesion, lbs./in.	2.6	PSTC-101F (30 min. applied)	pH of adhesive	+7*	Measured in liquid form	Photographic Activity Test	Passes	ISO 14523	LHAMA	16 CFR 1500.14(b)(8)	ASTM D4236	TRA	16 CFR 1500.3(b)(5) and (8)		Toy Safety	Complies ASTM F963-96a & Hasbro SRS-012 Rev F		Temperature Ranges			Minimum Application	+25°F (-4°C)	CTM #45 Curwood	Service Ranges	-75°F to +200°F (-59°C to +93°C)	Polyester Film Dry Surface	
Thickness, inches	0.0007 +/- 10%																															
Peel Adhesion, lbs./in.	2.6	PSTC-101F (30 min. applied)																														
pH of adhesive	+7*	Measured in liquid form																														
Photographic Activity Test	Passes	ISO 14523																														
LHAMA	16 CFR 1500.14(b)(8)	ASTM D4236																														
TRA	16 CFR 1500.3(b)(5) and (8)																															
Toy Safety	Complies ASTM F963-96a & Hasbro SRS-012 Rev F																															
Temperature Ranges																																
Minimum Application	+25°F (-4°C)	CTM #45 Curwood																														
Service Ranges	-75°F to +200°F (-59°C to +93°C)	Polyester Film Dry Surface																														
Liner	<p>A clay coated kraft lay flat liner for use in roll-to-sheet applications.</p> <table><tr><td>Caliper, inches</td><td>0.0032 +/- 10%</td><td>TAPPI T-411</td></tr><tr><td>Basis Weight, lbs. (24" x 36"/500 sheets)</td><td>44 +/- 10%</td><td>TAPPI T-410</td></tr></table>	Caliper, inches	0.0032 +/- 10%	TAPPI T-411	Basis Weight, lbs. (24" x 36"/500 sheets)	44 +/- 10%	TAPPI T-410																									
Caliper, inches	0.0032 +/- 10%	TAPPI T-411																														
Basis Weight, lbs. (24" x 36"/500 sheets)	44 +/- 10%	TAPPI T-410																														
Shelf Life	One year when stored at 72° F and 50% R.H.																															

CALL 1-800-548-3456 for additional product information



PERFORMANCE GUIDE

Represents Typical Values Only

www.Mactac.com

Lay Flat Guarantee: Guaranteed to exhibit layflat properties of no greater than $\pm 1/2$ " when evaluating an 8-1/2" x 11" sheet on a flat surface, face up orientation in a climate controlled (72°F / 50% RH) environment. It is recommended that this material be produced using 6" O. D. core to prevent core related roll set curl. Any products supplied on or rewound on other than 6" cores do not carry the layflat guarantee. Allow the material to acclimate to the environment for 72 hours before printing and converting.

CALL **1-800-548-3456** for additional product information

*Mactac knows of no standard that exists today for the determination of pH on a dried/coated pressure sensitive adhesive.

LHAMA - Labeling of Hazardous Art Materials Act

TRA - Toxicological Risk Assessment

This product complies with CONEG regulations.

All Mactac Roll Label products meet the requirements of the Clean Air Act of 1990.

Note: The user is responsible for determining the product's suitability for all aspects of the application. If there are any questions about applications or regulatory compliances, please contact your Mactac sales representative to discuss your requirements and recommendations. If this is a printed Performance Guide, it is an uncontrolled document. Please check the Mactac website for the latest, most up-to-date version.

IMPORTANT NOTICE: The information given and recommendations made herein are based on our research and are believed to be accurate. In every case, user shall determine before using any product in full scale production, whether such product is suitable for their particular purpose under their own operating conditions. User assumes all risk and liability whatsoever in connection with their use of any product. The products discussed herein are sold without any warranty as to merchantability or any other warranty, expressed or implied. No representative of ours has any authority to waive or change the foregoing provisions unless in a specific agreement signed by the officers of seller and manufacturer. Ultimately, sellers and manufacturers only obligation shall be to replace or credit such quantity of the product proved to be defective at its discretion.

TM Trademark of Morgan Adhesives Company LLC

® Registered Trademark of Morgan Adhesives Company LLC

