



PERFORMANCE GUIDE

Represents Typical Values Only

www.MACTac.com

CHG9592

Revised: 06/2019 RDF

Cast-coated High Gloss Opaque

Description	Applications and End Uses
Product CHG9592 is a 57# cast-coated high gloss facestock with a special opaque barrier and general-purpose permanent adhesive and a 2.4 semi-bleached super calendared kraft liner.	For labeling applications requiring a high gloss face stock with cover-up properties.
Face A 57# cast-coated, mirror finish, high strength paper stock designed for quality printing and high speed converting. Physical Properties Without Adhesive Caliper, inches 0.0036 +/- 10% TAPPI T-411 Brightness % Reflectance at 75°angle 86 TAPPI T-452 Opacity 99 TAPPI T-425 Gloss % Reflectance at 75°angle 83 TAPPI T-480 Tear, grams 22 MD 30 CD TAPPI T-414 Tensile, lbs./in. 35 MD 14 CD TAPPI T-494 Basis Weight, lbs. (25" x 38"/500) 57 +/- 10% TAPPI T-410	
Adhesive ST95 is a permanent acrylic emulsion with aggressive initial tack, excellent ultimate adhesion and mandrel hold. Very good adhesion to corrugated, glass and various plastic substrates. Considered to be latex glove friendly for use in some healthcare applications. Physical Properties of Adhesive Thickness, inches 0.0007 +/- 10% Peel Adhesion, lbs./in. 2.6 PSTC-101F (30 min. applied) Temperature Ranges Minimum Application +25°F (-4°C) CTM #45 Curwood Service Ranges -75°F to +200°F (-59°C to +93°C) Polyester Film Dry Surface	
Liner A semi-bleached super calendared kraft liner excellent for die cutting and stripping. The liner is coated with a release system designed specifically for label dispensing. Primarily for roll -to -roll applications. Caliper, inches 0.0024 +/- 10% TAPPI T-411 Basis Weight, lbs. (24" x 36"/500 sheets) 40 +/- 10% TAPPI T-410	
Shelf Life	One year when stored at 72° F and 50% R.H.

CALL 1-800-548-3456 for additional product information



PERFORMANCE GUIDE

Represents Typical Values Only

www.MACTac.com

Note: The user is responsible for determining the product's suitability for all aspects of the application. If there are any questions about applications or regulatory compliances, please contact your MACTac sales representative to discuss your requirements for recommendations. If this is a printed Performance Guide, it is an uncontrolled document. Please check the MACTac website for the latest version.

CALL 1-800-548-3456 for additional product information

IMPORTANT NOTICE: The information given and the recommendations made herein are based on our research and are believed to be accurate, but no guarantee of their accuracy or completeness is made. In every case, user shall determine before using any product in full scale production, or in any way, whether such product is suitable for user's intended use for their particular purpose under their own operating conditions. User assumes all risk and liability whatsoever in connection with their use of any product. The products discussed herein are sold without any warranty as to merchantability or fitness for a particular purpose, or any other warranty, express or implied. No representative of ours has any authority to waive or change the foregoing provisions, and no statement or recommendation not contained herein shall have any force of effect unless in an agreement signed by the officers of seller and manufacturer. Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent without authority from the owner of the patent. The following is made in lieu of all warranties, express or implied: Seller's and manufacturer's only obligation shall be to replace or credit such quantity of the product proved to be defective at its discretion.

TM Trademark of Morgan Adhesives Company.

® Registered Trademark of Morgan Adhesives Company.

