

PERFORMANCE GUIDE

**Represents Typical Values Only** 

www.Mactac.com

**DSS9501** 

Revised: 06/2019 RDF

## Durascan<sup>®</sup> S Thermal Transfer Film

Description			Applicatio	Applications and End Uses		
Product	DSS9501 is a 3.2 mil thermal transfer printable coated white biaxially oriented polyethylene with a permanent acrylic adhesive and a 2.4 semi-bleached super calendar kraft liner.		nt requiring du lar markets inc shipping, dr	Thermal transfer and prime labels requiring durability. Applications and markets include food, beverage, shipping, drum labels, piping, lumber appliances, carpet backing, pallets.		
Face	A high-density polyethylene film, clay coated to provide an excellent thermal transfer printing surface.					
	Physical Properties Without Adh	esive				
	Caliper, inches 0.		0.0032 (3.2 mils	s)	ASTM D-2103	
	Tensile, lbs./in. 2		23 MD 22 CD		TAPPI-494	
	Basis Weight, lbs. (25" x 38"/500 sheets)		44 +/- 10%	/- 10% TAPPI T-410		
	Considered to be latex glove frien	ndly for use in some	nealthcare applica	ations.	trates.	
	Considered to be latex glove frien Physical Properties of Adhesive Thickness, inches	0.0007 +/- 10%	nealthcare applica			
	Physical Properties of Adhesive Thickness, inches Peel Adhesion, lbs./in.		nealthcare applica		01A (30 min.	
	Physical Properties of Adhesive Thickness, inches	0.0007 +/- 10%		PSTC-10 applied CTM #4	01A (30 min. I) 45 Curwood ter Film Dry	
Liner	Physical Properties of Adhesive Thickness, inches Peel Adhesion, lbs./in. Temperature Ranges Minimum Application	0.0007 +/- 10% 2.6 +25°F (-4°C) -75°F to +200°F (-5 d kraft liner excellen	59°C to +93°C)	PSTC-10 applied CTM #4 Polyest Surface	01A (30 min. l) 45 Curwood ter Film Dry	
Liner	Physical Properties of Adhesive Thickness, inches Peel Adhesion, lbs./in. Temperature Ranges Minimum Application Service Ranges A semi-bleached super calendare	0.0007 +/- 10% 2.6 +25°F (-4°C) -75°F to +200°F (-5 d kraft liner excellen	59°C to +93°C)	PSTC-10 applied CTM #4 Polyest Surface stripping	01A (30 min. l) 45 Curwood ter Film Dry	
Liner	Physical Properties of Adhesive Thickness, inches Peel Adhesion, lbs./in. Temperature Ranges Minimum Application Service Ranges A semi-bleached super calendare Primarily for roll -to -roll applicat	0.0007 +/- 10% 2.6 +25°F (-4°C) -75°F to +200°F (-5 d kraft liner excellen ions.	59°C to +93°C) t for die cutting, s	PSTC-10 applied CTM #4 Polyest Surface stripping	01A (30 min. 1) 15 Curwood cer Film Dry 2 and label disp	

Durascan is a registered trademark of the Morgan Adhesives Company

Thermal transfer printing quality and bar code scannability are dependent upon the interworking of several elements; the ribbon, the printhead and the facestock. Please test all applications. Consult MACtac's Technical Marketing Department for guidelines regarding printer and ribbon compatibility.

Note: The user is responsible for determining the product's suitability for all aspects of the application. If there are any questions about applications, or regulatory compliances, please contact your MACtac sales representative to discuss your requirements for recommendations. If this is a printed Performance Guide, it is an uncontrolled document. Please check the MACtac website for the latest, most up-to-date version at <u>www.mactac.com</u>

**IMPORTANT NOTICE:** The information given and the recommendations made herein are based on our research and are believed to be accurate, but no guarantee of their accuracy or completeness is made. In every case, user shall determine before using any product in full scale production, or in any way, whether such product is suitable for user's intended use for their particular purpose under their own operating conditions. User assumes all risk and liability whatsoever in connection with their use of any product. The products discussed herein are sold without any warranty as to merchantability or fitness for a particular purpose, or any other warranty, express or implied. No representative of ours has any authority to waive or change the foregoing provisions, and no statement or recommendation not contained herein shall have any force of effect unless in an agreement signed by the officers of seller and manufacturer. Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent without authority from the owner of the patent. The following is made in lieu of all warranties, express or implied: Seller's and manufacturer's only obligation shall be to replace or credit such quantity of the product proved to be defective at its discretion.

<sup>™</sup> Trademark of Morgan Adhesives Company.

<sup>®</sup> Registered Trademark of Morgan Adhesives Company.

