



PERFORMANCE GUIDE

Represents Typical Values Only

www.Mactac.com

DTM8602

Revised 12/2017 KSM

Face Description

A **medium sensitivity** bright white direct thermal paper topcoated for optimum environmental resistance. Optimal wavelength range under 660nm.

Test Property	Typical Values	Test Method
Basis Weight 17 x 22 sheets	19# Avg.	TAPPI T-410
Caliper, inches	0.00295 +/- 10%	TAPPI T-411
Tear, grams	45 MD 40 CD	TAPPI-414
Tensile, lbs/in	29 MD 15 CD	TAPPI-494
Brightness %	89% Avg.	TAPPI T-525
Image Color	Black	
Initial Activation Temp (O.D.=0.2)		192 ± 9°F (89 ± 5°C)
Effective Activation Temp (O.D.=0.8)		221 ± 9°F (105 ± 5°C)
Optimum Activation Temp (O.D.=1.4)		225± 9°F (107 ± 5°C)
Resistance to Heat & Humidity		Outstanding
Resistance to Oils, Fats, Blood, Plasticizers		Excellent
15 Hour Water Immersion		Excellent

Adhesive Description MR860

MR860 is a general-purpose acrylic based removable adhesive with excellent long-term removability from a wide variety of surfaces. Always pretest removable adhesives for suitability in each particular end use application. Test extensively on corrugated substrates. NOT RECOMMENDED FOR MANDREL APPLICATIONS.

Test Property	Typical Values	Test Method
Caliper, inches	0.0007 +/- 10%	
Min Application	25°F (-4°C) on most surfaces	
Service range	-40 to 200°F (-40°C to 93°C)	
Peel Adhesion, pounds/in.	Stainless Steel = 0.7 Glass = 0.6 HDPE = 0.6 PVC = 0.8	PSTC-101/Method F (7 days applied)

When comparing values, keep in mind, other suppliers may use different testing methods.

Liner Description

A semi-bleached, super calendared kraft liner excellent for die cutting and stripping. The liner release system is designed specifically for label dispensing. Primarily for roll-to-roll applications.

Test Property	Typical Values	Test Method
Caliper	0.0024 +/- 10%	TAPPI T411
Basis Weight	40 +/- 10%	TAPPI T410

Applications

Used for barcode and human readable labels in retail and industrial markets where removable labels are required. Recommended for use in **standard speed** thermal printers.

Shelf Life

One year when stored at 72°F and 50% RH. For more about Direct Thermal Storage, see the Technical Bulletin for Direct Thermal Storage at www.mactac.com.

Note: The user is responsible for determining the product's suitability for all aspects of the application. If there are any questions about applications, regulatory compliances, please contact your MACTac sales representative to discuss your requirements for recommendations. If this is a printed Performance Guide, it is an uncontrolled document. Please check the MACTac website for the latest, most up-to-date version at www.mactac.com

CALL 1-800-548-3456 for additional product information

IMPORTANT NOTICE: The information given and the recommendations made herein are based on our research and are believed to be accurate, but no guarantee of their accuracy or completeness is made. In every case, user shall determine before using any product in full scale production, or in any way, whether such product is suitable for user's intended use for their particular purpose under their own operating conditions. User assumes all risk and liability whatsoever in connection with their use of any product. The products discussed herein are sold without any warranty as to merchantability or fitness for a particular purpose, or any other warranty, express or implied. No representative of ours has any authority to waive or change the foregoing provisions, and no statement or recommendation not contained herein shall have any force of effect unless in an agreement signed by the officers of seller and manufacturer. Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent without authority from the owner of the patent. The following is made in lieu of all warranties, express or implied: Seller's and manufacturer's only obligation shall be to replace or credit such quantity of the product proved to be defective at its discretion.

TM Trademark of Morgan Adhesives Company.

® Registered Trademark of Morgan Adhesives Company.

