



PERFORMANCE GUIDE

Represents Typical Values Only

www.Mactac.com

GF9002-78 Vivid™ 3 Clear Polystyrene

Revised: 06/2017 KSM

Description	Applications and End Uses			
Product	GF9002-78 is a 2.0 mil clear polystyrene film with a quick tack permanent adhesive and a 2.4 mil semi-bleached super calendared kraft liner. The entire construction converts and prints on wider webs and higher-speeds than typical rubber based adhesive coated papers.	General-purpose clear film applications. Converts and dispenses easily. Ideal base stock for coupon labels.		
Face	Optically clear high gloss polystyrene is corona treated for printing. Designed for indoor use as a coupon base and as a primary label in non-conformable applications. Smooth containers should be used in labeling applications to avoid air bubble entrapment with automatic dispensing.			
	Physical Properties Without Adhesive			
	Caliper	2.0 mils	ASTM D2103	
	Tensile at Yield (MD/CD)	22.4/21.0 PPIW	ASTM D882	
	Tensile at Break (MD/CD)	24.5/22.0 PPIW	ASTM D882	
	Elongation at Yield	4.6/5.0%	ASTM D882	
	Elongation at Break (MD/CD)	48.5/5.0%	ASTM D882	
	1% Secant Modulus (MD/CD)	390,000/386,500 PSI	ASTM D882	
	Tear Strength (MD/CD)	21/35	ASTM D1922	
Adhesive	710VHP is a permanent, rubber-based adhesive with excellent tack and ultimate adhesion to a variety of surfaces including polystyrene, polypropylene, polyethylene, paper and corrugate. Suitable for cold, damp labeling applications. Very good high speed and wider web converting.			
	Physical Properties of Adhesive			
	Thickness, inches	0.0007 +/- 10%		
	Peel Adhesion, lbs./in.	Corrugate: 1.3	PSTC-1 (30 min. applied)	
		HDPE: 1.8	PSTC-1 (30 min. applied)	
		Stainless Steel: 2.7	PSTC-1 (30 min. applied)	
	Loop Tack (1"), lbs./in.	Corrugate: 2.3	CTM-25	
		HDPE: 3.2	CTM-25	
		Stainless Steel: 4.8	CTM-25	
	Temperature Ranges			
	Minimum Application	+20°F (-7°C)	CTM #45 Curwood	
	Service Ranges	-65°F to +160°F (-54°C to +71°C)	Polyester Film Dry Surface	
Liner	A semi-bleached super calendared kraft liner excellent for die cutting, stripping and label dispensing. Primarily for roll -to -roll applications.			
	Caliper, inches	0.0024 +/- 10%	TAPPI T-411	
	Basis Weight, lbs. (24" x 36"/500 sheets)	40 +/- 10%	TAPPI T-410	
Shelf Life	One year when stored at 72° F and 50% R.H.			

Opticlear® is a registered trademark of Morgan Adhesives Company

This product complies with CONEG regulations.

All MACTac Roll Label products meet the requirements of the Clean Air Act of 1990.

The user is responsible for determining the product's suitability for all aspects of the application. If there are any questions about applications, or regulatory compliances, please contact your MACTac sales representative to discuss your requirements for recommendations. If this is a printed Performance Guide, it is an uncontrolled document. Please check the MACTac website for the latest, most up-to-date version at www.mactac.com

CALL 1-800-548-3456 for additional product information

IMPORTANT NOTICE: The information given and the recommendations made herein are based on our research and are believed to be accurate, but no guarantee of their accuracy or completeness is made. In every case, user shall determine before using any product in full scale production, or in any way, whether such product is suitable for user's intended use for their particular purpose under their own operating conditions. User assumes all risk and liability whatsoever in connection with their use of any product. The products discussed herein are sold without any warranty as to merchantability or fitness for a particular purpose, or any other warranty, express or implied. No representative of ours has any authority to waive or change the foregoing provisions, and no statement or recommendation not contained herein shall have any force of effect unless in an agreement signed by the officers of seller and manufacturer. Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent without authority from the owner of the patent. The following is made in lieu of all warranties, express or implied: Seller's and manufacturer's only obligation shall be to replace or credit such quantity of the product proved to be defective at its discretion.

TM Trademark of Morgan Adhesives Company.

® Registered Trademark of Morgan Adhesives Company.

