# **TECHNICAL DATA SHEET\***



mactac.com

### **PF7002**

## Vivid™ 2 Mil Polypropylene

Description

**Product** 

Face: 2 Mil Clear Polypropylene

Adhesive: 711VHP Liner: 2.4 SCK Total Construction Caliper (Approx):

**5.1** mils +/- 10%

Revised: 7/2/2024

**Face** 

Vivid™ is a 2 mil clear polypropylene film top-coated film for superior graphics. Economic alternative where ultra-clarity is needed. Not recommended for outdoor use.

Physical Properties	Typical Value	<b>Test Method</b>
Caliper	0.002 " +/- 10%	ASTM D2103
Elongation at Break, % (YIELD)	168 MD 75 CD	ASTM D1922
Tensile, lbs/in (YIELD)	17 MD 26 CD	ASTM D589
Opacity		ASTM D882

### **Adhesive**

711VHP is a cold temperature, permanent, rubber-based adhesive with excellent tack and ultimate adhesion to a wide variety of surfaces, including most packaging films. It can also be used in food contact label applications. FDA approved for direct food contact under 21 CFR Section 175.125(a) and (b).

Physical Properties	Typical Value	Test Method	
180° Peel Adhesion			
Stainless Steel	2.7 lbs / in	PSTC-101A (30 min. applied)	
HDPE	2.2 lbs / in	PSTC-101A (30 min. applied)	
Loop Tack			
Stainless Steel	4.7 <b>l</b> bs / in	PSTC-16A	
HDPE	3.1 lbs / in	PSTC-16A	
Temperature Ranges			
Minimum Application Temperature	+20°F (-7°C)		
Service Temperature	-65°F to +160°F (-54°C to +71°C)		
isclaimer: Tested with 2.6 mil white BOPP film facestock at roc	om temperature on standard lab	panels. The service temperature listed is subject	

**Disclaimer:** Tested with 2.6 mil white BOPP film facestock at room temperature on standard lab panels. The service temperature listed is subject to limitations of the facestock and substrate used.

### Liner

A super calendared kraft liner excellent for die cutting, stripping and label dispensing. Primarily for roll-to-roll applications.

Physical Properties	Typical Value	Test Method
Caliper	0.0024 " +/- 10%	TAPPI T-411
Basis Weight	39.9 lbs. +/- 10%	TAPPI T-410

**Shelf Life** One year from the date of shipment, when stored at 72°F and 50% relative humidity.

The user is responsible for determining the product's suitability for all aspects of the application. If there are any questions about applications, or regulatory compliances please contact your Mactac sales representative to discuss your requirements for recommendations. If this is a printed Technical Data Sheet, it is an uncontrolled document. Please check the Mactac website for the latest, most-up-to-date version. The products discussed herein are sold without any warranty as to merchantability or any other warranty, expressed or implied.

Call 1-800-548-3456 for additional product information or visit www.mactac.com

<sup>\*</sup>This document represents typical values and is not considered a specification.