

PERFORMANCE GUIDE

Represents Typical Values Only

Revised: 07/2019 RDF

www.mactac.com

PJ1691-0 (Developmental RDT16141)

2.6 mil White Polypropylene / PUREtac CL216 / 1 mil PET

Description	scription			Applications and End Uses		
Product	PJ1691-0 is a 2.6 mil white top coated Polypropylene film (Label-Lyte®) with a quick tack permanent adhesive designed for prime film labeling and a 1 mil PET liner.		For prime labeling applications requiring the durability and aesthetics of film. Recommended for semi-rigid and rigid containers. Market segments: food, cosmetic, toiletries, household cleaners, beverage and more.			
Adhesive	This white top coated pearlescent polypropylene is a semi conformable film designed for excellent printing, converting and label dispensing. Print test product and consult with your ink supplier to confirm suitability for your application.					
	Physical Properties Without Adhes	ive				
	Caliper, inches		0.0026 (2.6 n	nil)	ASTM D2103	
	Opacity		88%		ASTM D589	
	Tensile, lbs./in. (YIELD)		14 MD 80 CE)	ASTM D882	
	Elongation, % (YIELD)		12 MD 45 C)	ASTM D1922	
	Suitable for cold, damp labeling app Physical Properties of Adhesive Thickness, inches	0.0007 +/- 10%	cca and wider	WCD CONVE	urig.	
	180° Peel Adhesion, lbs.,	·		PSTC-101	A	
		HDPE: 3.5				
		Stainless Steel: 3.9				
		LDPE: 3.2				
		Glass: 3.8				
	Loop Tack (1"), lbs./in.		PSTC-16			
		HDPE: 2.9				
		HDPE: 2.9 Stainless Steel: 5.3				
		_				
		Stainless Steel: 5.3				
	Temperature Ranges	Stainless Steel: 5.3 LDPE: 2.6 Glass: 5.2				
	Minimum Application	Stainless Steel: 5.3 LDPE: 2.6 Glass: 5.2 +32°F (0°C)	. 174°C)		Curwood	
Liner	Minimum Application Service Ranges A 1 mil clear polyester liner excelle	Stainless Steel: 5.3 LDPE: 2.6 Glass: 5.2 +32°F (0°C) -50°F to +160°F (-46°C to not for die cutting, stripping a		Polyeste	Curwood r Film Dry Surface	
Liner	Minimum Application Service Ranges	Stainless Steel: 5.3 LDPE: 2.6 Glass: 5.2 +32°F (0°C) -50°F to +160°F (-46°C to not for die cutting, stripping a		Polyeste sing.		

Shelf Life One year when stored at 72° F and 50% R.H.

This product complies with CONEG regulations. All MACtac Roll Label products meet the requirements of the Clean Air Act of 1990.

Note: The user is responsible for determining the product's suitability for all aspects of the application. If there are any questions about applications, or regulatory compliances, please contact your MACtac sales representative to discuss your requirements for recommendations. If this is a printed Performance Guide, it is an uncontrolled document. Please check the MACtac website for the latest, most up-to-date version at www.mactac.com

IMPORTANT NOTICE: The information given and the recommendations made herein are based on our research and are believed to be accurate, but no guarantee of their accuracy or completeness is made. In every case, user shall determine before using any product in full scale production, or in any way, whether such product is suitable for user's intended use for their particular purpose under their own operating conditions. User assumes all risk and liability whatsoever in connection with their use of any product. The products discussed herein are sold without any warranty as to merchantability or fitness for a particular purpose, or any other warranty, express or implied. No representative of ours has any authority to waive or change the foregoing provisions, and no statement or recommendation not contained herein shall have any force of effect unless in an agreement signed by the officers of seller and manufacturer. Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent without authority from the owner of the patent. The following is made in lieu of all warranties, express or implied: Seller's and manufacturer's only obligation shall be to replace or credit such quantity of the product proved to be defective at its discretion.

 $^{\text{TM}}$ Trademark of Morgan Adhesives Company.



Registered Trademark of Morgan Adhesives Company.