



PERFORMANCE GUIDE

Represents Typical Values Only

PJ9001

Vivid™ 2.6 White Polypropylene

Revised: 12/2017 KSH

Description	Applications and End Uses
Product A 2.6 mil topcoated white biaxially oriented polypropylene (Label-Lyte®) with a quick tack permanent adhesive and a 2.4 semi-bleached super calendared kraft liner. The entire construction converts and prints on wider webs and higher-speeds than typical rubber based adhesive coated papers.	For prime labeling applications requiring the durability and aesthetics of film. Recommended for semi-rigid and rigid containers. Market segments: food, cosmetic, toiletries, household cleaners, beverage and more.
Face This white topcoated pearlescent polypropylene is a semi conformable film designed for excellent printing, converting and label dispensing. Print test product and consult with your ink supplier to confirm suitability for your application.	
Physical Properties Without Adhesive	
Caliper, inches	0.0026 +/- 10% ASTM D2103
Elongation, % (YIELD)	12 MD 45 CD ASTM D1922
Tensile, lbs./in. (YIELD)	14 MD 80 CD ASTM D882
Opacity	88% ASTM D589
Adhesive 710VHP is a permanent, rubber-based adhesive with excellent tack and ultimate adhesion to a variety of surfaces including polystyrene, polypropylene, polyethylene, paper and corrugate. Suitable for cold, damp labeling applications. Exceptional high speed and wider web converting.	
Physical Properties of Adhesive	
Thickness, inches	0.0007 +/- 10%
Peel Adhesion, lbs./in.	Corrugate: 1.3 PSTC-101A (30 min. applied) HDPE: 1.8 Stainless Steel: 2.7
Loop Tack (1"), lbs./in.	Corrugate: 2.3 PSTC-16 HDPE: 3.2 Stainless Steel: 4.8
Temperature Ranges	
Minimum Application	+20°F (-7°C) CTM #45 Curwood
Service Ranges	-65°F to +160°F (-54°C to +71°C) Polyester Film Dry Surface
Liner A semi-bleached super calendared kraft liner excellent for die cutting, stripping and label dispensing. Primarily for roll -to -roll applications.	
Caliper, inches	0.0024 +/- 10% TAPPI T-411
Basis Weight, lbs. (24" x 36"/500 sheets)	39.5 +/- 10% TAPPI T-410
Shelf Life	One year when stored at 72° F and 50% R.H.

Polyfilm® is a registered Trademark of the Morgan Adhesives Company

Label-Lyte® is a registered Trademark of the ExxonMobil Company

This product complies with CONEG regulations.

All MACTac Roll Label products meet the requirements of the Clean Air Act of 1990.

The user is responsible for determining the product's suitability for all aspects of the application. If there are any questions about applications, or regulatory compliances, please contact your MACTac sales representative to discuss your requirements for recommendations. If this is a printed Performance Guide, it is an uncontrolled document. Please check the MACTac website for the latest, most up-to-date version at www.mactac.com

IMPORTANT NOTICE: The information given and the recommendations made herein are based on our research and are believed to be accurate, but no guarantee of their accuracy or completeness is made. In every case, user shall determine before using any product in full scale production, or in any way, whether such product is suitable for user's intended use for their particular purpose under their own operating conditions. User assumes all risk and liability whatsoever in connection with their use of any product. The products discussed herein are sold without any warranty as to merchantability or fitness for a particular purpose, or any other warranty, express or implied. No representative of ours has any authority to waive or change the foregoing provisions, and no statement or recommendation not contained herein shall have any force of effect unless in an agreement signed by the officers of seller and manufacturer. Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent without authority from the owner of the patent. The following is made in lieu of all warranties, express or implied: Seller's and manufacturer's only obligation shall be to replace or credit such quantity of the product proved to be defective at its discretion.

TM Trademark of Morgan Adhesives Company.

® Registered Trademark of Morgan Adhesives Company.

