

TECHNICAL DATA SHEET*

mactac.com

PJ9012

Vivid™ 2.6 Mil Gloss Polypropylene

Description

Product

Face: 2.6 Mil Gloss Polypropylene

Adhesive: 710VHP

Liner: 3.2 SCK

Total Construction

Caliper (Approx): **6.5** mils +/- 10%

Face This white, top-coated pearlescent polypropylene is a semi-conformable film designed for excellent printing, converting and label dispensing. Print test product and consult with your ink supplier to confirm suitability for your application. Meets APR Critical Guidance Criteria for use with high-density polyethylene (HDPE) containers.

Physical Properties

Caliper

Typical Value

0.0026 " +/- 10%

Test Method

ASTM D2103

Elongation at Break, % (YIELD)

177 MD 42 CD

ASTM D1922

Tensile, lbs/in (YIELD)

13 MD 27 CD

ASTM D589

Opacity

86

ASTM D882

Adhesive 710VHP is a permanent, rubber-based adhesive with excellent tack and ultimate adhesion to a variety of surfaces including polystyrene, polypropylene, polyethylene, paper and corrugate. Suitable for cold, damp labeling applications. Very good high speed and wider web converting.

Physical Properties

180° Peel Adhesion

Typical Value

Test Method

Stainless Steel

2.7 lbs / in

PSTC-101A (30 min. applied)

HDPE

2.2 lbs / in

PSTC-101A (30 min. applied)

Loop Tack

Stainless Steel

4.7 lbs / in

PSTC-16A

HDPE

3.1 lbs / in

PSTC-16A

Temperature Ranges

Minimum Application Temperature

+20°F (-7°C)

Service Temperature

-65°F to +160°F (-54°C to +71°C)

Disclaimer: Tested with 2.6 mil white BOPP film facestock at room temperature on standard lab panels. The service temperature listed is subject to limitations of the facestock and substrate used.

Liner A semi-bleached calendared kraft liner excellent for die cutting, stripping and label dispensing. Primarily for roll-to-roll applications, where a more demanding liner may be needed.

Physical Properties

Caliper

Typical Value

0.0032 " +/- 10%

Test Method

TAPPI T-411

Basis Weight

52.5 lbs. +/- 10%

TAPPI T-410

Shelf Life One year from the date of shipment, when stored at 72°F and 50% relative humidity.

*This document represents typical values and is not considered a specification.

The user is responsible for determining the product's suitability for all aspects of the application. If there are any questions about applications, or regulatory compliances please contact your Mactac sales representative to discuss your requirements for recommendations. If this is a printed Technical Data Sheet, it is an uncontrolled document. Please check the Mactac website for the latest, most-up-to-date version. The products discussed herein are sold without any warranty as to merchantability or any other warranty, expressed or implied.

Call **1-800-548-3456** for additional product information or visit **www.mactac.com**