

www.mactac.com

SGL2602

Revised: 07/2022 KSH

Platinum™ Bright Semi-Gloss

Description	Applications and End Uses		
Product	SGL2602 is a 55# bright white semi-gloss coated litho construction with a general-purpose permanent adhesive and a 2.4 semi-bleached super calendared kraft liner.	For prime labeling applications in several markets: food, cosmetic, beverage, household cleaners and more.	
Face	55# Platinum High Bright Semi-Gloss is a brilliant white semi-gloss coated sheet with outstanding ink receptivity and high internal strength characteristics for high speed printing and converting. The sheet has exceptional smoothness, whiteness, gloss and opacity.		
	Physical Properties Without Adhesive		
	Caliper, inches	0.0027 +/- 10%	TAPPI T-411
	Brightness % Reflectance at 75° angle	88	TAPPI T-452
	Gloss % Reflectance at 75° angle	75	TAPPI T-480
	Opacity	86	TAPPI T-425
	Parker Smoothness	1.0	TAPPI T-555
	Tear, grams	40 MD 45 CD	TAPPI T-414
	Tensile, lbs./in.	32 MD 15 CD	TAPPI T-494
	Gurley Stiffness	89 MD 54 CD	TAPPI T-543
	Basis Weight, lbs. (25" x 38"/500 sheets)	55 +/- 10%	TAPPI T-410
Adhesive	An all temperature acrylic adhesive that performs well in normal to freezer temperature applications. 640AT exhibits some open time on some substrates (please test) and develops a permanent bond to a wide variety of substrates.		
	Physical Properties of Adhesive		
	Thickness, inches	0.0007 +/- 10%	
	Peel Adhesion, lbs./in.	1.8	PSTC-101F (30 min. applied)
	Temperature Ranges		
	Minimum Application	-20° F (-29°C) on most surfaces	
	Service Ranges	-65 to +200° F (-54 to +93°C)	
Liner	A semi-bleached super calendared kraft liner excellent for die cutting, stripping and label dispensing. Primarily for roll-to-roll applications.		
	Caliper, inches	0.0024 +/- 10%	TAPPI T-411
	Basis Weight, lbs. (24" x 36"/500 sheets)	40 +/- 10%	TAPPI T-410
Shelf Life	One year when stored at 72° F and 50% R.H.		

This product complies with CONEG regulations.

All MACTac Roll Label products meet the requirements of the Clean Air Act of 1990.

Note: The user is responsible for determining the product's suitability for all aspects of the application. If there are any questions about applications, or regulatory compliances, please contact your MACTac sales representative to discuss your requirements for recommendations. If this is a printed Performance Guide, it is an uncontrolled document. Please check the MACTac website for the latest, most-up-to-date version.

CALL 1-800-548-3456 for additional product information

IMPORTANT NOTICE: The information given and the recommendations made herein are based on our research and are believed to be accurate, but no guarantee of their accuracy or completeness is made. In every case, user shall determine before using any product in full scale production, or in any way, whether such product is suitable for user's intended use for their particular purpose under their own operating conditions. User assumes all risk and liability whatsoever in connection with their use of any product. The products discussed herein are sold without any warranty as to merchantability or fitness for a particular purpose, or any other warranty, express or implied. No representative of ours has any authority to waive or change the foregoing provisions, and no statement or recommendation not contained herein shall have any force of effect unless in an agreement signed by the officers of seller and manufacturer. Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent without authority from the owner of the patent. The following is made in lieu of all warranties, express or implied: Seller's and manufacturer's only obligation shall be to replace or credit such quantity of the product proved to be defective at its discretion.

TM Trademark of Morgan Adhesives Company.

[®] Registered Trademark of Morgan Adhesives Company.

