

# PERFORMANCE GUIDE

#### www.Mactac.com



## Starliner®

Updated 06/08

## Teslin - Permanent

Stock Numbers

8½" x 11" SL 2321

SL 2323

26" x 20"

SL 2322

17" x 22"

SL 2324

12" x 18"

### Construction

Face: Adhesive: Liner: 7 mil Teslin SP-700 MP2003 Permanent Acrylic

Specially processed scored release liner. Back

printed in red "Starliner Permanent"

Applications and End Uses

For applications requiring abrasion and moisture resistance. Last up to 6 month in outdoor applications. Applications include drum labels,

POP and bumper stickers.

## Description

Face

7-mil Teslin SP-700 white synthetic paper is designed for applications combining the appearance of paper with superior moisture and abrasion resistance.

Typical Physical Properties of Face Stock without Adhesive

TAPPI T-414 75 MD Tear, grams. Tensile, lbs./in. 11 MD 6 CD **TAPPI T-494**  $0.0071 \pm (7.1 \text{ mils})$ Caliper: inches TAPPI T-411

Adhesive

Liner

MP2003 is an acrylic emulsion with aggressive initial tack and excellent ultimate adhesion to corrugated, glass, fiber drums and various plastic substrates and other common substrates. Patented non-ooze characteristics will provide clean kiss, die, and guillotine cutting.

**Typical Physical Properties of Adhesive** 

TAPPI T-411 Thickness, inches 0.0008 +/- 10%

Peel Adhesion, lbs./in. 3.0 PSTC-2 (30 min. applied)

A nominal 80# white kraft liner has excellent lay-flat characteristics and internal strength, toughness,

Temperature Ranges

+45°F (7°C) CTM #45 Curwood Minimum Application Polyester Film Dry Surface

Service Ranges -65°F to +150°F (-54°C to +66°C)

tear resistance for kiss cutting.

**Typical Physical Properties of Liner** 

Caliper, inches 0.0042+/- 10% TAPPI T-411 Basis Weight, lbs. (24" x 36"/500 sheets) 72 +/- 10% TAPPI T-410

**Total Caliper**  $0.0125 \pm 10\%$  inches (12.5 mils) 255 g/m<sup>2</sup>

## **Printing Process**

Printable by offset-lithography and screen-printing process with ink systems compatible with this product. All inks used on this product should be 100% oxidizing. Avoid all glycol, glycerin and citric acid based fountain solutions. Micron size of anti set-off powders should be 35-50. Stacks in delivery should not exceed 1.5". All over coats such as UV, aqueous and varnish coatings should be tested prior to production run. The liner utilized on this product is guaranteed line copy printable by one color only. It is NOT recommended for process or multiple color heavy coverage printing. UV screen or offset printing may cause the liner to curl. Compatible with HP Indigo presses. Follow printer manufacturer's recommendations for printing pressure sensitive media. A Teflon fuser roll is recommended due to heavy adhesive coat weight. Testing is recommended.

**Shelf Life** 

One year when stored at 72° F and 50% R.H.

IMPORTANT NOTICE: The information given and the recommendations made herein are based on our research and are believed to be accurate, but no guarantee of their accuracy or completeness is made. In every case, user shall determine before using any product in full scale production, or in any way, whether such product is suitable for user's intended use for their particular purpose under their own operating conditions. User assumes all risk and liability whatsoever in connection with their use of any product. The products discussed herein are sold without any warranty as to merchantability or fitness for a particular purpose, or any other warranty, express or implied. No representative of ours has any authority to waive or change the foregoing provisions, and no statement or recommendation not contained herein shall have any force of effect unless in an agreement signed by the officers of seller and manufacturer. Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent without authority from the owner of the patent. The following is made in lieu of all warranties, express or implied: Seller's and manufacturer's only obligation shall be to replace or credit such quantity of the product proved to be defective at its discretion.

™ Trademark of Morgan Adhesives Company.

Registered Trademark of Morgan Adhesives Company. Teslin SP-700 is a registered trademark of PPG Industries Indigo is a registered trademark of Hewlett Packard

