

# GS Rivet Tapes

## Engineered Tapes & Laminates



Appliance/  
White Goods

Building &  
Construction

Industrial &  
Fabrication

Sign &  
Display

Transportation &  
Recreational  
Vehicles



**macbond®**

**mactac®**  
A LINTEC COMPANY



# GS Rivet Tapes

## Engineered Tapes & Laminates

### Features

- Solvent-free, high-strength, rubber, pressure sensitive adhesive
- Available in 5.0 mil to 50 mil thickness
- Available in 0.5" to 11.5" adhesive widths
- Rolls are manufactured with ungummed edges for ease of application
- MTO & custom sizes will ship in 10-15 working days

### Benefits

- Immediate bond to most surfaces from smooth to textured.
- Extremely durable and able to replace mechanical fasteners in many applications
- Thinner coatings are ideal for POP or craft assembly, thicker coatings are ideal for panel assembly, vibration dampening and moisture resistance.
- Acts as a third hand in many assembly applications.
- Ideal for use with metal, wood, polyethylene, polypropylene, glass and corrugated materials.

Part Number	Adhesive	Caliper (Mils) Adhesive	Adhesive Width	Liner Width	Roll Length	MOQ Rolls	Rolls/ Carton	Stock/ MTO
GS1001	GS Ultra High Tack	20	1.00"	1.50"	200'	8	8	Stock
GS1003	GS Ultra High Tack	20	.50"	1.00"	200'	12	12	Stock
GS1004	GS Ultra High Tack	35	.50" (RR)	2.00"	200'	6	6	Stock
GS1007	GS Ultra High Tack	35	1.00"	1.50"	200'	8	8	Stock
GS1013	GS Ultra High Tack	20	2.00"	3.00"	200'	4	4	Stock
GS1019	GS Ultra High Tack	35	0.75"	1.50"	200'	96	8	MTO
GS1023	GS Ultra High Tack	15	1.00"	1.50"	200'	96	8	MTO
GS2123200	GS Ultra High Tack	10	2.00"	3.00"	200'	36	4	MTO
GS2145-SC	GS Ultra High Tack	10	4.00"	5.00"	1350'	16	16*	MTO
GS2003	GS Ultra High Tack	5	0.75"	1.20"	900'	30	10	MTO
GS2004	GS Ultra High Tack	5	1.00"	1.50"	900'	24	8	MTO
GS2208	GS Ultra High Tack	15	4.00"	6.00"	400'	36	2	MTO
GS2313	GS Ultra High Tack	20	1.00"	1.20"	200'	120	10*	MTO
GS2603RR	GS Ultra High Tack	35	(2) @ .75" (RR)	3.00"	200'	48	4	MTO
GS2906	GS Ultra High Tack	50	2.00"	2.40"	150'	160	10	MTO

(RR)= 2 lanes of adhesive      \* Packed on pallets

### Performance Characteristics

Test	Units	Typical Values
Quick Tack	lbs/sq in	20+
Peel Adhesion	lbs/in	22+
Shear	hours to fail	300+
Application Temp	degrees F	+50
Service Temp	degrees F	0 to 180

For Regulatory Information, please visit [www.mactac.com](http://www.mactac.com) for all product regulatory compliance.

For Quality information, please visit [www.mactac.com/quality](http://www.mactac.com/quality) for all manufacturing site ISO 9001 certificates.

For Technical Data Sheets please visit [www.mactac.com/industrialtapes](http://www.mactac.com/industrialtapes).

Mactac is a member of the following organizations:

Gasket Fabricators Association  
Pressure Sensitive Tape Council



Customer Service 800-548-3456

Mactac North America | 4560 Darrow Road, Stow, OH 44224-1898

email [mactac.americas@mactac.com](mailto:mactac.americas@mactac.com) • [www.mactac.com/industrialtapes](http://www.mactac.com/industrialtapes)