



PERFORMANCE GUIDE

Represents Typical Values Only

www.Mactac.com

PF3791-0 (Currently RDT20110-5)

Revised: 10/2020 KSH

2.0 mil Clear Polypropylene / PUREapply / 1.2 mil PET

Description	Applications and End Uses			
Product	PF3791-0, is a 2.0 mil clear top coated polypropylene film with a quick tack permanent adhesive designed for initial removability of misapplied labels and a 1.0 mil PET liner.	For prime labeling applications requiring the durability and aesthetics of film. Recommended for semi-rigid and rigid containers. Market segments: food, cosmetic, toiletries, household cleaners, beverage and more.		
Face	A 2 mil clear top coated polypropylene semi conformable film designed for excellent printing, converting and label dispensing. Print test product and consult with your ink supplier to confirm suitability for your application.			
	Physical Properties Without Adhesive			
	Caliper, inches	0.002 (2.0 mil)	ASTM D2103	
	Tensile, lbs./in. (YIELD)	15 MD 68 CD	ASTM D882	
	Elongation, % (YIELD)	12 MD 48 CD	ASTM D1922	
Adhesive	Mactac PUREapply is a clear, permanent, rubber-based adhesive with excellent tack and ultimate adhesion to a variety of surfaces. PUREapply is engineered to have initial removability on HDPE, polyester, polypropylene and glass. It exhibits exceptional clarity and resistance to water whitening. Suitable for cold, damp labeling applications. Very good high speed and wider web converting.			
	Physical Properties of Adhesive			
	Thickness, inches	0.0007 +/- 10%		
	180° Peel Adhesion, lbs./in.		PSTC-101A	
		HDPE: 2.5		
		Polypropylene: 2.5		
		Glass: 3.3		
		PET: 3.5		
	Loop Tack (1"), lbs./in.		PSTC-16	
		HDPE: 2.6		
		Polypropylene: 2.4		
		Glass: 5.6		
		PET: 5.4		
	Temperature Ranges			
	Minimum Application	+10°F (-12°C)	CTM #45 Curwood	
	Service Ranges	-50°F to +175°F (-46°C to +79°C)	Polyester Film Dry Surface	
Liner	A 1.0 mil clear polyester liner excellent for die cutting, stripping and label dispensing. Primarily for roll-to-roll applications.			
	Caliper, inches	0.00092 +/- 10%	TAPPI T-411	
	Basis Weight, lbs. (24" x 36"/500 sheets)	20.1 +/- 10%	TAPPI T-410	
Shelf Life	One year when stored at 72° F and 50% R.H.			

This product complies with CONEG regulations. All MACTac Roll Label products meet the requirements of the Clean Air Act of 1990.

Note: The user is responsible for determining the product's suitability for all aspects of the application. If there are any questions about applications, or regulatory complian ces, please contact your MACTac sales representative to discuss your requirements for recommendations. If this is a printed Performance Guide, it is an uncontrolled document. Please check the MACTac website for the latest, most up-to-date version at www.mactac.com

CALL 1-800-548-3456 for additional product information

IMPORTANT NOTICE: The information given and the recommendations made herein are based on our research and are believed to be accurate, but no guarantee of their accuracy or completeness is made. In every case, user shall determine before using any product in full scale production, or in any way, whether such product is suitable for user's intended use for their particular purpose under their own operating conditions. User assumes all risk and liability whatsoever in connection with their use of any product. The products discussed herein are sold without any warranty as to merchantability or fitness for a particular purpose, or any other warranty, express or implied. No representative of ours has any authority to waive or change the foregoing provisions, and no statement or recommendation not contained herein shall have any force of effect unless in an agreement signed by the officers of seller and manufacturer. Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent without authority from the owner of the patent. The following is made in lieu of all warranties, express or implied: Seller's and manufacturer's only obligation shall be to replace or credit such quantity of the product proved to be defective at its discretion.

TM Trademark of Morgan Adhesives Company.

[®] Registered Trademark of Morgan Adhesives Company.

