

TECHNICAL DATA SHEET*

mactac.com

PJ7212

Vivid™ 2.6 Mil White Polypropylene

Description

Product

Face: 2.6 Mil White Polypropylene

Total Construction

Caliper (Approx): 6.5 mils +/- 10%

Adhesive: 711VHP

Liner: 3.2 SCK

Face	This white, top-coated pearlescent polypropylene is a semi-conformable film designed for excellent printing, converting and label dispensing. Print test product and consult with your ink supplier to confirm suitability for your application. Meets APR Critical Guidance Criteria for use with high-density polyethylene (HDPE) containers.
-------------	---

Physical Properties	Typical Value	Test Method
Caliper	0.0026 " +/- 10%	ASTM D2103
Elongation at Break, % (YIELD)	177 MD 42 CD	ASTM D1922
Tensile, lbs/in (YIELD)	13 MD 27 CD	ASTM D589
Opacity	86	ASTM D882

Adhesive	711VHP is a cold temperature, permanent, rubber-based adhesive with excellent tack and ultimate adhesion to a wide variety of surfaces, including most packaging films. 711VHP may be used as the food contact surface of labels and/or tapes applied to poultry, dry food, and processed, frozen, dried, partial dehydrated and raw fruits and vegetables. FDA approved for direct food contact under 21 CFR Section 175.125(a) and (b).
-----------------	---

Physical Properties	Typical Value	Test Method
180° Peel Adhesion		
Stainless Steel	2.7 lbs / in	PSTC-101A (30 min. applied)
HDPE	2.2 lbs / in	PSTC-101A (30 min. applied)
Loop Tack		
Stainless Steel	4.7 lbs / in	PSTC-16A
HDPE	3.1 lbs / in	PSTC-16A
Temperature Ranges		
Minimum Application Temperature	+20°F (-7°C)	
Service Temperature	-65°F to +160°F (-54°C to +71°C)	

Disclaimer: Tested with 2.6 mil white BOPP film facestock at room temperature on standard lab panels. The service temperature listed is subject to limitations of the facestock and substrate used.

Liner	A semi-bleached calendered kraft liner excellent for die cutting, stripping and label dispensing. Primarily for roll-to-roll applications, where a more demanding liner may be needed.
--------------	--

Physical Properties	Typical Value	Test Method
Caliper	0.0032 " +/- 10%	TAPPI T-411
Basis Weight	52.5 lbs. +/- 10%	TAPPI T-410

Shelf Life	One year from the date of shipment, when stored at 72°F and 50% relative humidity.
-------------------	--

*This document represents typical values and is not considered a specification.

The user is responsible for determining the product's suitability for all aspects of the application. If there are any questions about applications, or regulatory compliances please contact your Mactac sales representative to discuss your requirements for recommendations. If this is a printed Technical Data Sheet, it is an uncontrolled document. Please check the Mactac website for the latest, most-up-to-date version. The products discussed herein are sold without any warranty as to merchantability or any other warranty, expressed or implied.

Call **1-800-548-3456** for additional product information or visit www.mactac.com