

www.mactac.com

PJ7752-7

Rev: 12/2020 CNS

Vivid™ 2.6 Mil White Polypropylene

Description	Applications and End Uses		
Product	PJ7752-7 A 2.6 mil topcoated white biaxially oriented polypropylene (Label-Lyte®) with a quick tack All Temp permanent, direct food contact adhesive and a 1.7 mil glassine liner.		
Face	This white topcoated pearlescent polypropylene is a semi conformable film designed for excellent printing, converting and label dispensing. Print test product and consult with your ink supplier to confirm suitability for your application.		
	Physical Properties Without Adhesive		
	Caliper, inches	0.0026 +/- 10%	ASTM D2103
	Elongation, % (YIELD)	12 MD 45 CD	ASTM D1922
	Tensile, lbs./in. (YIELD)	14 MD 80 CD	ASTM D882
	Opacity	88%	ASTM D589
Adhesive	Chill AT FDA is an All Temp permanent, rubber-based adhesive, direct food contact adhesive that performs well in normal to freezer temperature applications. Chill has excellent tack and ultimate adhesion to a variety of surfaces including polystyrene, polypropylene, polyethylene, paper and corrugate. Suitable for cold, damp labeling applications.		
	FDA approved for direct food contact under 21 CFR Section 175.125(a) and (b). Section 175.125(a) pertains to adhesive that are "used as the food-contact surface of labels and/or tapes applied to poultry, dry food, and processed, frozen, dried, or partially dehydrated fruits or vegetables". Section 175.125(b) pertains to adhesives that are "used as the food-contact surface of labels and/or tapes applied to raw fruit and raw vegetables".		
	Physical Properties of Adhesive		
	Thickness, inches	0.0007 +/- 10%	
	180° Peel Adhesion, lbs./in.	Corrugate: 2.6	PSTC-101A (30 min. applied)
		HDPE: 3.6	PSTC-101A (30 min. applied)
		Stainless Steel: 3.6	PSTC-101A (30 min. applied)
	Loop Tack (1"), lbs./in.	Corrugate: 1.6	PSTC-16
		HDPE: 2.3	PSTC-16
		Stainless Steel: 4.9	PSTC-16
	Temperature Ranges		
	Minimum Application	-10°F (-23.33°C)	CTM #45 Curwood
	Service Ranges	-65°F to +150°F (-54°C to 65.6°C)	Polyester Film Dry Surface
Liner	A glassine liner excellent for die cutting, stripping and label dispensing. Primarily for roll-to-roll applications.		
	Caliper, inches	0.0016 +/- 10%	TAPPI T-411
	Basis Weight, lbs. (24" x 36"/500 sheets)	27.7 +/- 10%	TAPPI T-410
Shelf Life	One year when stored at 72° F and 50% R.H.		

Polyfilm® is a registered Trademark of the Morgan Adhesives Company

Label-Lyte® is a registered Trademark of the ExxonMobil Company

This product complies with CONEG regulations.

All MACTac Roll Label products meet the requirements of the Clean Air Act of 1990.

The user is responsible for determining the product's suitability for all aspects of the application. If there are any questions about applications, or regulatory compliances, please contact your MACTac sales representative to discuss your requirements for recommendations. If this is a printed Performance Guide, it is an uncontrolled document.

Please check the MACTac website for the latest, most up-to-date version at www.mactac.com

CALL 1-800-548-3456 for additional product information

IMPORTANT NOTICE: The information given, and recommendations made herein are based on our research and are believed to be accurate. In every case, user shall determine before using any product in full scale production, whether such product is suitable for their particular purpose under their own operating conditions. User assumes all risk and liability whatsoever in connection with their use of any product. The products discussed herein are sold without any warranty as to merchantability or any other warranty, expressed or implied. No representative of ours has any authority to waive or change the foregoing provisions unless in a specific agreement signed by the officers of seller and manufacturer. Ultimately, sellers and manufacturers only obligation shall be to replace or credit such quantity of the product proved to be defective at its discretion.

™ Trademark of Morgan Adhesives Company LLC
® Registered Trademark of Morgan Adhesives Company LLC
www.mactac.com

