

TECHNICAL DATA SHEET*

mactac.com

PJL9552-4

Vivid™ 2.4 Mil White Polypropylene

Description

Product

Face: 2.4 Mil White Polypropylene

Adhesive: ST95

Liner: 2.1 Glassine

Total Construction

Caliper (Approx): **5.2** mils +/- 10%

Face This white top-coated, pearlescent biaxially oriented polypropylene is a semi-conformable film designed for excellent printing, converting and label dispensing. Proprietary top coating delivers excellent adhesion for superior graphics and print receptivity for various methods including UV Flexo, Water Flexo, Gravure, UV Inkjet, and Hot Stamp.

Physical Properties

Caliper
Elongation at Break, % (YIELD)
Tensile, lbs/in (YIELD)
Opacity

Typical Value

0.0024 " +/- 10%
170 MD 35 CD
14 MD 29 CD
90

Test Method

ASTM D2103
ASTM D1922
ASTM D589
ASTM D882

Adhesive ST95 is a general-purpose permanent acrylic emulsion with aggressive initial tack, excellent ultimate adhesion and mandrel hold. Very good adhesion to corrugated, glass, and various plastic substrates. Also used in healthcare applications and considered to be latex glove friendly.

Physical Properties

180° Peel Adhesion
Stainless Steel
HDPE

Loop Tack
Stainless Steel
HDPE

Typical Value

2.5 lbs / in
1.8 lbs / in

3.2 lbs / in
2.2 lbs / in

Test Method

PSTC-101A (30 min. applied)
PSTC-101A (30 min. applied)

PSTC-16A
PSTC-16A

Temperature Ranges

Minimum Application Temperature
Service Temperature

+25°F (-4°C)
-75°F to +200°F (-59°C to +93°C)

Disclaimer: Tested with 2.6 mil white BOPP film facestock at room temperature on standard lab panels. The service temperature listed is subject to limitations of the facestock and substrate used.

Liner 65# clay coated one side (C1S) white kraft liner designed for and commonly used in roll-to-sheet applications.

Physical Properties

Caliper
Basis Weight

Typical Value

0.0021 " +/- 10%
35.3 lbs. +/- 10%

Test Method

TAPPI T-411
TAPPI T-410

Shelf Life One year from the date of shipment, when stored at 72°F and 50% relative humidity.

*This document represents typical values and is not considered a specification.

The user is responsible for determining the product's suitability for all aspects of the application. If there are any questions about applications, or regulatory compliances please contact your Mactac sales representative to discuss your requirements for recommendations. If this is a printed Technical Data Sheet, it is an uncontrolled document. Please check the Mactac website for the latest, most-up-to-date version. The products discussed herein are sold without any warranty as to merchantability or any other warranty, expressed or implied.

Call **1-800-548-3456** for additional product information or visit **www.mactac.com**