

PERFORMANCE GUIDE

Represents Typical Values Only

www.mactac.com

FSC® SG7892-2 Created: 03/2023 MLS

Platinum Bright Semi-Gloss

Description		Applications and End Uses Ideal for high quality prime labeling applications for food packaging and cold damp substrates.			
Product	SG7892-2 is a 54# brilliant white semi-gloss coated litho construction with a quick tack All Temp permanent adhesive and a 1.2 mil PET liner. FSC Certified. Certificate Number: FSC-C161021.				
Face	54# Platinum High Bright Semi-Gloss is a brilliant white semi-gloss coated sheet with outstanding ink receptivity and high internal strength characteristics for high speed printing and converting. The sheet has exceptional smoothness, whiteness, gloss and opacity.				
Adhesive	Physical Properties Without Adhesive				
	Caliper, inches		0.0027 +/- 10%		TAPPI T-411
	Brightness % Reflectance at 75° angle		88		TAPPI T-452
	Gloss % Reflectance at 75° angle		75		TAPPI T-480
	Opacity		86		TAPPI T-425
	Parker Smoothness	Parker Smoothness			TAPPI T-555
	Tear, grams		40 MD 45 CD		TAPPI T-414
	Tensile, lbs./in.		32 MD 15	CD	TAPPI T-494
	Gurley Stiffness		89 MD 54 CD		TAPPI T-543
	Basis Weight, lbs. (25" x 3	88"/500 sheets)	55+/- 10%		TAPPI T-410
	temperature applications. Chill has excellent tack and ultimate adhesion to a variety of surfaces including polystyrene, polypropylene, polyethylene, paper and corrugate. Suitable for cold, damp labeling applications.				
	Physical Properties of Adhesive Thickness, inches	0.0007 +/- 10%			
	Peel Adhesion, lbs./in.	Corrugate: 1.4		PSTC-101F (30 min. applied)	
		HDPE: 1.7			
		Stainless Steel: 2.6			
	Loop Tack (1"), lbs./in.	Corrugate: 1.85		PSTC-16	
		HDPE: 2.6			
		Stainless Steel: 4.1			
	Temperature Ranges				
	Minimum Application Service Ranges	-10°F (-23.33°C) -65°F to +150°F (-54°C†	to 65.6°C)	CTM #45 Curwood 5°C) Polyester Film Dry Surface	
Liner	 mil clear polyester liner excellent for die cutting, stripping and label dispensing. Primarily for roll-to-roll applications. 				
	Caliper, inches		0.0012 +/-	10%	TAPPI T-411
Chalf I :fa	One week when stared at 72° F and	1 F.O.O./ D.I.I.			

Shelf Life

One year when stored at 72° F and 50% R.H.

This product complies with CONEG regulations.

All MACtac Roll Label products meet the requirements of the Clean Air Act of 1990.

IMPORTANT NOTICE: The information given, and the recommendations made herein are based on our research and are believed to be accurate, but no guarantee of their accuracy or completeness is made. In every case, user shall determine before using any product in full scale production, or in any way, whether such product is suitable for user's intended use for their particular purpose under their own operating conditions. User assumes all risk and liability whatsoever in connection with their use of any product. The products discussed herein are sold without any warranty as to merchantability or fitness for a particular purpose, or any other warranty, express or implied. No representative of ours has any authority to waive or change the foregoing provisions, and no statement or recommendation not contained herein shall have any force of effect unless in an agreement signed by the officers of seller and manufacturer. Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent without authority from the owner of the patent. The following is made in lieu of all warranties, express or implied: Seller's and manufacturer's only obligation shall be to replace or credit such quantity of the product proved to be defective at its discretion.

 $^{\text{TM}}$ Trademark of Morgan Adhesives Company.



[®] Registered Trademark of Morgan Adhesives Company.