



www.MACtac.com

PERFORMANCE GUIDE

Represents Typical Values Only

SGL7792-2

Revised: 02/2025 MTT

FSC® Platinum™ XTRA Semi-Gloss CHILL AT FDA 1.2 mil PET

Description

Product

SGL7792-2 is a 55# brilliant white semi-gloss coated litho construction with a quick tack, direct food contact adhesive and a 1.2 mil PET liner.

Applications and End Uses

Adhesive in compliance for direct food for dry fruits and vegetables.

Face

Platinum XTRA is a 55# basis weight, brilliant white semi-gloss coated sheet with outstanding ink receptivity and high internal strength characteristics for high speed printing and converting. The sheet has exceptional smoothness, whiteness, gloss and opacity.
FSC Certified. Certificate Number: SCS-COC-007635

Physical Properties Without Adhesive

Caliper, inches	0.003 +/- 10%	TAPPI T-411
Brightness % Reflectance at 75° angle	88	TAPPI T-452
Gloss % Reflectance at 75° angle	75	TAPPI T-480
Opacity	86	TAPPI T-425
Parker Smoothness	0.90	TAPPI T-555
Tear, grams	40 MD 45 CD	TAPPI T-414
Tensile, lbs./in.	32 MD 15 CD	TAPPI T-494
Gurley Stiffness	89 MD 54 CD	TAPPI T-543
Basis Weight, lbs. (25" x 38"/500 sheets)	55+/- 10%	TAPPI T-410

Adhesive

CHILL AT FDA is an all-temperature permanent, rubber-based adhesive that performs well in normal to freezer temperature applications. Chill AT FDA has excellent tack and ultimate adhesion to a variety of surfaces and may be used as the food contact surface of labels and/or tapes applied to poultry, dry food, and processed, frozen, dried, partial dehydrated and raw fruits and vegetables. Suitable for cold, damp labeling applications

FDA approved for direct food contact under 21 CFR Section 175.125(a) and (b). Section 175.125(a) pertains to adhesive that are "used as the food-contact surface of labels and/or tapes applied to poultry, dry food, and processed, frozen, dried, or partially dehydrated fruits or vegetables". Section 175.125(b) pertains to adhesives that are "used as the food-contact surface of labels and/or tapes applied to raw fruit and raw vegetables".

Physical Properties of Adhesive

Thickness, inches	0.0007 +/- 10%	
Peel Adhesion, lbs./in.	Corrugate: 1.4 HDPE: 1.7 Stainless Steel: 2.6	PSTC-101F (30 min. applied)
Loop Tack (1"), lbs./in.	Corrugate: 1.85 HDPE: 2.6 Stainless Steel: 4.1	PSTC-16

Temperature Ranges

Minimum Application	-10°F (-23°C)
Service Ranges	-65°F to +150°F (-54°C to 65.6°C)

The user is responsible for determining the product's suitability for all aspects of the application. If there are any questions about applications, or regulatory compliances, please contact your MACtac sales representative to discuss your requirements for recommendations. If this is a printed Performance Guide, it is an uncontrolled document. Please check the MACtac website for the latest, most-up-to-date version.

CALL 1-800-548-3456 for additional product information or visit www.mactac.com



www.MACtac.com

PERFORMANCE GUIDE

Represents Typical Values Only

Liner	1.2 mil clear polyester liner ideally suited for maximum strength in very high speed automatic dispensing for roll to roll applications. Caliper, inches	0.0012 +/- 10%	TAPPI T-411
--------------	---	----------------	-------------

Shelf Life	One year when stored at 72° F and 50% R.H
-------------------	---

The user is responsible for determining the product's suitability for all aspects of the application. If there are any questions about applications, or regulatory compliances, please contact your MACtac sales representative to discuss your requirements for recommendations. If this is a printed Performance Guide, it is an uncontrolled document. Please check the MACtac website for the latest, most-up-to-date version.

CALL **1-800-548-3456** for additional product information or visit **www.mactac.com**

IMPORTANT NOTICE: The information given and the recommendations made herein are based on our research and are believed to be accurate, but no guarantee of their accuracy or completeness is made. In every case, user shall determine before using any product in full scale production, or in any way, whether such product is suitable for user's intended use for their particular purpose under their own operating conditions. User assumes all risk and liability whatsoever in connection with their use of any product. The products discussed herein are sold without any warranty as to merchantability or fitness for a particular purpose, or any other warranty, express or implied. No representative of ours has any authority to waive or change the foregoing provisions, and no statement or recommendation not contained herein shall have any force of effect unless in an agreement signed by the officers of seller and manufacturer. Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent without authority from the owner of the patent. The following is made in lieu of all warranties, express or implied: Seller's and manufacturer's only obligation shall be to replace or credit such quantity of the product proved to be defective at its discretion.

TM Trademark of Morgan Adhesives Company.

[®] Registered Trademark of Morgan Adhesives Company.

